

Black annealed steel wire



- Annealed wire for paper, cardboard and waste baling presses with automatic tie-off.
- Chemical composition (%):
 - C: 0,08 max.
 - Mn: 0,30 - 0,60
 - Si: 0,20 max.
 - P: 0,035 max.
 - S: 0,035 max.
- Resistance: 36 - 38 kg/mm² (± 3 kg/mm²).
- Elongation (%): 35 - 42 minimum



Coil Dimensions

Ø Wire	Weight	Ø Interior	Ø Exterior	h
1,3 mm - 3,9 mm	200 kg	450 mm	850 mm	300 mm
2,7 mm - 3,9 mm	500 kg	450 mm	850 mm	450 mm
2,7 mm - 3,9 mm	750 kg	450 mm	850 mm	550 mm
3,0 mm - 3,9 mm	1000 kg	450 mm	850 mm	800 mm

Sizes and weights

Ø Wire (mm)	Metres in 1 kg.	Grams. in 1 m.
2,40	28,16	35,50
2,70	22,25	44,90
3,00	18,02	55,50
3,20	15,84	63,10
3,40	14,03	71,30
3,70	11,85	84,40
3,90	10,66	93,80



Exel Fil, S.A.
Apdo. de Correos 129
Polígono Industrial s/n
25200 Cervera (Spain)
Tel. + (34) 97 353 22 12
Fax + (34) 97 353 28 09
exelfil@exelfil.com
www.exelfil.com

Sales office / Export
Ganduxer, 127 bajos
08022 Barcelona (Spain)
Tel. + (34) 93 253 17 22
Fax + (34) 93 253 05 83
export@exelfil.com
www.exelfil.com